

# **Confidential Report**

Our Ref: 27/06174/06/23







Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0) 113 259 1999

Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 4 July 2023

Our Ref: 27/06174/06/23

Your Ref: ---

Page: 1 of 10

Client:	Nu-Coat Limited
CIICIIL.	Nu-Coat Ellille

A1/2 Chapel Farm Industrial Estate Cwmcarn Caerphilly Newport NP11 7BH

Job Title: Fire Classification of One Sample of Self Adhesive Vinyl Material

Clients Order Ref: POR01014

Date of Receipt: 9 June 2023

Description of Sample: One sample of vinyl material, referenced; M63-X-X (self adhesive product).

Work Requested: We were asked to make the following test(s):

BS EN 13501-1

- subcontracted test, UKAS accredited
- \*\* subcontracted test, EN ISO/IEC 17025 accredited
- \*\*\* not UKAS accredited





Note: This report relates only to the items tested.



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 4 July 2023

Our Ref: 27/06174/06/23 Your Ref:

> Page: 2 of 10

Client: **Nu-Coat Limited** 

## FIRE TESTS ACCORDING TO BS EN ISO 11925-2:2020

Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame – Part 2 Single-flame source test.

Date of Test: 03/07/2023

## **Conditioning**

Test specimens and filter paper conditioned as described in BS EN 13238:2010.

#### **Procedure**

The tested in accordance with BS ΕN ISO 11925-2. sampled sample was The sponsor the material and the specimens were cut to the dimensions stated.

Three length and three width specimens were prepared in accordance with the above standard. Specified filter paper was placed beneath the specimen holder and replaced between tests.

The specimens were mounted vertically in the specimen holder so that one end and both sides were enclosed with the exposed end 30mm from the end of the frame. The burner was inclined at an angle of 45°.

The flame height was set at 20 mm with the flame impinging on the specimen for 30 seconds on the centre line, 40 mm above the bottom edge.

A marker was placed 150 mm above the upper end of the burner and the time recorded when the flame tip reached the marker, if applicable. The following parameters were also recorded:-

- 1. If ignition occurs
- 2. Presence of flaming debris, if applicable
- 3. Ignition of the filter paper, if applicable







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

4 July 2023 Date:

Our Ref: 27/06174/06/23 Your Ref:

Page: 3 of 10

**Client: Nu-Coat Limited** 

## **Duration of test**

For a flame application time of 30 seconds, the total test duration is 60 seconds after application of the flame.

## **Classification Criteria**

The samples were classified according to BS EN 13501-1:2018 Fire classification of Construction Products and Building Elements: Part 1: Classification using Test Data from Reaction to Fire Tests.

For construction products excluding floorings to meet the performance criteria taken from Table 1:

Classification	Classification Criteria (mean values)		
E	Fs ≤ 150mm within 20 seconds		
F	Fails Class E		

Classification Classification criteria for flaming drop		
	5 1	
None	Pass = no ignition of paper	
d-2	Fail = Ignition of paper	







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

4 July 2023 Date:

Our Ref: 27/06174/06/23 Your Ref:

> Page: 4 of 10

**Client: Nu-Coat Limited** 

## **Results**

The test results relate to the behaviour of the test specimens of a material under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

Specimen   Ignition (Yes or No)		Tip of flame reaches 150mm		Flaming droplets		
		•	Yes or No	Time taken (s)	Yes or No	Ignition of Filter paper (Yes or No)
	1	Yes	No	N/A	No	No
Machine 2 Direction	Yes	No	N/A	No	No	
3		Yes	No	N/A	No	No
Across 1 Machine 2 Direction 3	1	Yes	No	N/A	No	No
	2	Yes	No	N/A	No	No
	3	Yes	No	N/A	No	No

## Note

Sample was tested as an essentially flat product, the specimens were tested self adhered onto a 12mm calcium silicate board as defined in BS EN 13238:2010. A surface exposure was carried out only.

Test BS EN ISO 11925-2:2020 is accredited under our flexible scope policy.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk Website: www.bttg.co.uk

Date: 4 July 2023

Our Ref: 27/06174/06/23 Your Ref: ---

Page: 5 of 10

Client: Nu-Coat Limited

## **Photograph of Specimen**









Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 4 July 2023

Our Ref: 27/06174/06/23 Your Ref:

> Page: 6 of 10

Client: **Nu-Coat Limited** 

#### FIRE TESTS ACCORDING TO BS EN 13823:2020

Reaction to fire tests for Building Products - Building Products excluding floorings exposed to the thermal attack by a single burning item. Classified According to BS EN 13501-1:2018

Date of Test: 03/07/2023

## **Conditioning**

The specimens were conditioned in accordance with BS EN 13238:2010.

## **Principle**

Test specimens, consisting of two vertical wings forming a right-angled corner, is exposed to the flames of a burner placed at the bottom of that corner. The flames are obtained by the combustion of propane gas, injected through a sandbox to give a heat output of 30.7±2.0kW.

The performance of the test specimen is evaluated over a period of 20 minutes. The performance requirements are: heat production, smoke production, lateral flame spread and falling flaming droplets and particles.

The heat production is measured by use of oxygen calorimeter that uses the principle that the amount of oxygen consumed in a fire is proportional to the amount of heat produced. The smoke production is measured by use of a light attenuation instrument installed in the exhaust duct alongside the sampling equipment used to measure the heat release. Visual observations are made of the horizontal flame spread and falling of flaming droplets and particles.







Page:

Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 4 July 2023

Our Ref: 27/06174/06/23 Your Ref:

7 of 10

Client: **Nu-Coat Limited** 

#### **Procedure**

The test was carried out in accordance with BS EN 13823:2020.

Each specimen was tested self adhered onto a 12mm calcium silicate board as defined in BS EN 13238:2010.

Each specimen was placed in the trolley as per the instructions given and placed underneath the hood in the testing chamber. The volume flow of the exhaust was set to 0.60±0.05 m<sup>3</sup>/s and maintained at this throughout the test period.

The temperatures in the exhaust hood and the ambient temperature should be within 4°C with the ambient temperature being within 20±10°C. The other pre-test conditions of ambient pressure and ambient relative humidity were also recorded.

The recording of baseline data is started at 0 s. At 120 s the auxiliary burner is ignited and the propane mass flow adjusted to the specified flow before 150 s, this flow to be kept constant throughout the test.

With the pre-test conditions met, the propane supply is switched from the auxiliary burner to the main burner at 300 s.

The burning behaviour of the specimen was recorded both automatically and visually over a period of 1,260 s from when the main burner was ignited.

At 1560 s the gas supply was terminated along with the automatic recording of the data. The conditions at the end of the test were recorded at least one minute after any remaining combustion has been totally extinguished.

The individual pre-test and baseline conditions, apparatus specifications, test validity criteria, burner details was found to be within specified parameters. The graphs of HRR, HRR(30), THR, FIGRA, SPR, SPR(60), TSP and SMOGRA are found below with the results and classification.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

4 July 2023 Date:

Our Ref: 27/06174/06/23 Your Ref:

> Page: 8 of 10

**Client: Nu-Coat Limited** 

## **Classification Criteria**

The samples were classified according to BS EN 13501:2018 Fire classification of Construction Products and Building Elements: Part 1: Classification using Test Data from Reaction to Fire Tests.

For construction products excluding floorings the classes are:

Classification	Classification Criteria (mean values)			
Classification	FIGRA <sub>0.2MJ</sub> (W/s) FIGRA <sub>0.4MJ</sub> (W/s)		LFS	THR <sub>600s</sub> (MJ)
A2	≤120	N/A	Edge of specimen	≤7.5
В	≤120	N/A	Edge of specimen	≤7.5
С	N/A	≤250	Edge of specimen	≤15
D	N/A	≤750	No requirement	No requirement

To meet classification A2 the sample also has to meet the requirements of either BS EN ISO 1182 or BS EN ISO 1716.

To meet classification B, C and D the sample also has to meet the requirements of BS EN ISO 11925-2.

Additional Classifications - Smoke and Flaming droplets/particles

Classification	Classification Criteria (mean values)		
Classification	SMOGRA (m <sup>2</sup> /s <sup>2</sup> )	TSP <sub>600s</sub> (m <sup>2</sup> )	
s1	≤30	≤50	
s2	≤180	≤200	
s3	Not s1 or s2	Not s1 or s2	
d0	No flaming droplets/particles within 600seconds		
d1	No flaming droplets/particles persisting longer than 10 seconds		
uı	within 600 seconds		
d2	Not d0 or d1		







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 4 July 2023

Our Ref: 27/06174/06/23 Your Ref:

> 9 of 10 Page:

Client: **Nu-Coat Limited** 

#### **Results**

Classification criteria		Specimen			Class
Classification Criteria	1	2	3	Mean	Class
FIGRA <sub>0.2MJ</sub> (W/s)	0.0	8.8	7.2	5.3	
FIGRA <sub>0.4MJ</sub> (W/s)	0.0	8.8	7.2	5.3	В
THR <sub>600s</sub> (MJ)	1.2	1.3	1.3	1.3	В
LFS to edge (yes or no)	No	No	No	No	
SMOGRA (m <sup>2</sup> /s <sup>2</sup> )	0.0	0.0	9.1	3.0	•3
TSP <sub>600s</sub> (m <sup>2</sup> )	48.9	52.3	54.0	51.7	<b>s2</b>
FDP flaming ≤ 10 s (yes or no)	No	No	No	No	40
FDP flaming > 10 s (yes or no)	No	No	No	No	d0

## **Note**

The test results relate to the behaviour of the test specimen of a product under the particular conditions of the test; they are not intended to be the sole criteria for assessing the potential fire hazard of the product in use.

Test BS EN 13823:2020 is accredited under our flexible scope policy.

## Comment

The results meet the requirements of a possible Class B, s1, d0 but a definite Class B, s2, d0, as specified in BS EN 13501-1:2018.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (https://www.bttg.co.uk/about-us/decision-rules-policy/) for further information.

Reported by:..... ...... G Harvey (Mr), Laboratory Technician

..... A Shute, Section Leader Countersigned by:.....

Enquiries concerning this report should be addressed to Customer Services.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 4 July 2023

27/06174/06/23 Our Ref:

Your Ref:

Page: 10 of 10

**Client: Nu-Coat Limited** 

# **Uncertainty Budget**

The uncertainty budget for BS EN 13501-1:2018 was determined as follows:-

## BS EN ISO 11925-2:2020

±2 seconds for time recorded removal of flame and terminate test

#### BS EN 13823:2020

FIGRA 0.2MJ	±15%
FIGRA 0.4MJ	±15%
THR 600s	±10%
SMOGRA	±15%
TSP 600s	±20%



