



| | | | | | |
|---------------------------|---|-----------------|-------|---------------|-----|
| Description | M12-P-X. 80µ gloss white high-opacity 5 year monomeric PVC, airXit permanent adhesive, stay flat structured neutral PE liner 'M Series' 5 year monomeric for flat-sides. High opacity bright white monomeric with an 'airXit' clear permanent adhesive on a polyethylene coated liner. The structured liner and adhesive systems speeds up application times and helps to eliminate air bubbles. High opacity coverall film is the preferred alternative to a grey adhesive. EN13501-1 and BS 476 Class 0 fire rated. | | | | |
| Key Features | Solvent, Latex and UV printable. For flat mid term surfaces. Fire rated. Bubble free dry application. Available up to 1600mm wide. Phthalate Free VOC Free | | | | |
| Conversion | Primarily for digital printing but can be CAD cut. Prints should be left flat for at least 4 hours prior to cutting, lamination or application. | | | | |
| Precaution | For application to flat surfaces only. | | | | |
| Application | Dry application. | | | | |
| Compliance | REACH and RoHS compliant | | | | |
| Fire Certification | EN13501-1 and BS 476 Class 0 | | | | |
| Face Material | Monomeric high-opacity calendered PVC | | | | |
| Face Thickness | 80µ thick | | | | |
| Adhesive | 'airXit' PermPLUS permanent clear UV polyacrylate - VOC Free | | | | |
| Adhesive weight | Nominal 25gsm | | | | |
| Perceived Tack | Medium Tack Repositionable / Permanent | | | | |
| Liner | 150gsm structured PE liner | | | | |
| Dimensional stability | Nominal 0.13mm | | | | |
| Conformability | 1D Flat-sided | | | | |
| Optimal application temp | +15 to 25°C | | | | |
| Min application temp | +10°C | | | | |
| Max application temp | +30°C | | | | |
| Intermittent service temp | -30 to 100°C | | | | |
| Shelf-life | 2 year | | | | |
| Adhesive Data (Nominal) | 180° Peel Adhesion N/25mm | | | | |
| | | Stainless Steel | Glass | Polypropylene | MDF |
| | 20 min | 12 | 13 | 7 | 4 |
| | 24 hour | 12 | 13 | 8 | 5 |
| | 1 week | 13 | 14 | 8 | 6 |
| Chemical Resistance | The unprinted film can be wiped clean with water and diluted household detergents. Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali, diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc. | | | | |
| Outdoor Durability | 5 year unprinted Zone 1 (Northern Europe, North America) vertical exposure 2-3 year unprinted Zone 2 (S. Europe, Central & S. America, Asia Pacific) vertical exposure 1-2 year unprinted Zone 3 (Middle East, Africa & desert areas) vertical exposure | | | | |
| Important | The nominal values shown are based upon research and test methods on unprinted material and are provided without guarantee and do not constitute a warranty. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Actual performance will depend on substrate preparation, exposure conditions and correct application. For further information on the test methods used refer to www.nu-coat.com/testmethods . Nu-Coat Limited will not be liable for any indirect or consequential loss. | | | | |