



Description	P11-P-P. 75µ gloss white 7 year polymeric PVC, PermPLUS permanent adhesive, stay flat PE liner. 'P Series' 7 year polymeric for simple curved surfaces. Bright white polymeric with a clear PermPLUS permanent adhesive on a stay flat PE liner.				
Key Features	Solvent, Latex and UV printable. For long term curved surfaces. PE liner for maximum stability. No adhesive milking when wet applied. Available up to 1600mm wide.				
Conversion	Primarily for digital printing but can be CAD cut. Prints should be left flat for at least 4 hours prior to cutting, lamination or application.				
Precaution	For application to flat and simple curved surfaces.				
Application	Dry or Wet application.				
Compliance	REACH and RoHS compliant				
Fire Certification	Self-extinguishing				
Face Material	Polymeric calendered PVC				
Face Thickness	75µ thick				
Adhesive	'PermPLUS' permanent clear UV polyacrylate				
Adhesive weight	Nominal 24gsm				
Perceived Tack	Medium Tack Permanent				
Liner	140gsm PE liner				
Dimensional stability	Nominal 0.09mm				
Conformability	2D Simple Curves				
Optimal application temp	+15 to 25°C				
Min application temp	+10°C				
Max application temp	+30°C				
Intermittent service temp	-30 to 100°C				
Shelf-life	2 year				
Adhesive Data (Nominal)	180° Peel Adhesion N/25mm				
		Stainless Steel	Glass	Polypropylene	MDF
	20 min	19	21	5	5
	24 hour	23	25	6	8
1 week	24	26	7	9	
Chemical Resistance	The unprinted film can be wiped clean with water and diluted household detergents. Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali, diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.				
Outdoor Durability	7 year unprinted Zone 1 (Northern Europe, North America) vertical exposure 3-4 year unprinted Zone 2 (S. Europe, Central & S. America, Asia Pacific) vertical exposure 2-3 year unprinted Zone 3 (Middle East, Africa & desert areas) vertical exposure				
Important	The nominal values shown are based upon research and test methods on unprinted material and are provided without guarantee and do not constitute a warranty. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Actual performance will depend on substrate preparation, exposure conditions and correct application. For further information on the test methods used refer to www.nu-coat.com/testmethods . Nu-Coat Limited will not be liable for any indirect or consequential loss.				