



Description	P65-W-P. 75µ silver crystal 5 year polymeric PVC, WindowPLUS permanent adhesive, stay flat neutral PE liner 'W Series' 5 year polymeric for window graphics, featuring a non-milking, when wet applied, WindowPLUS permanent adhesive. Adhesive builds bonds fast, even in wet and cold conditions, allowing application tape to be removed quickly. The 'water-repellent' PE coated liner makes wet application easier. Blocks over 65% of harmful UVA light, very good stability and light transmission, and good privacy.				
Key Features	For mid term flat surfaces. UVA block 65%. Solvent, Latex and UV printable. 'Water-repellent' PE liner for maximum stability. No adhesive milking when wet applied. Available up to 1530mm wide.				
Conversion	Primarily for CAD. For Latex printing, users are advised to test print. Prints must be left flat and uncovered for at least 4 hours prior to cutting, lamination, application.				
Precaution	There is always a risk of leaving adhesive during removal. Adhesive residue is reduced if wet application is used.				
Application	Wet application is highly recommended.				
Compliance	REACH and RoHS compliant				
Fire Certification	Self-extinguishing				
Face Material	Polymeric calendered PVC				
Face Thickness	75µ thick				
Adhesive	'WindowPLUS' permanent clear UV polyacrylate				
Adhesive weight	Nominal 24gsm				
Perceived Tack	Medium Tack Permanent				
Liner	140gsm PE liner				
Dimensional stability	Nominal 0.06mm				
Conformability	2D Simple Curves				
Optimal application temp	+5 to 25°C				
Min application temp	+2°C on stainless steel or glass				
Max application temp	+30°C				
Intermittent service temp	-30 to 100°C				
Shelf-life	2 year				
Adhesive Data (Nominal)	180° Peel Adhesion N/25mm				
		Stainless Steel	Glass	Polypropylene	MDF
	20 min	12	14	8	4
	24 hour	16	17	10	5
1 week	17	18	12	6	
Chemical Resistance	The unprinted film can be wiped clean with water and diluted household detergents. Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali, diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.				
Outdoor Durability	5 year unprinted Zone 1 (Northern Europe, North America) vertical exposure 2-3 year unprinted Zone 2 (S. Europe, Central & S. America, Asia Pacific) vertical exposure 2 year unprinted Zone 3 (Middle East, Africa & desert areas) vertical exposure				
Important	The nominal values shown are based upon research and test methods on unprinted material and are provided without guarantee and do not constitute a warranty. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Actual performance will depend on substrate preparation, exposure conditions and correct application. For further information on the test methods used refer to www.nu-coat.com/testmethods . Nu-Coat Limited will not be liable for any indirect or consequential loss.				