

Description	<p>S11-Z Cling2 150µ gloss white static PVC, 190gsm neutral PE cling liner</p> <p>Cling2 White is a smooth, gloss white phthalate free highly plasticised monomeric calendered PVC film formulated for use with leading roll fed printers and sheet fed presses. For self-cling internal and external graphics on windows and other smooth surfaces. Print side face out.</p>			
Key Features	<p>No adhesive so no adhesive residue on removal. Adheres well to smooth surfaces. Available up to 1370mm wide. Solvent, Latex and UV printable. Splice free rolls.</p>			
Conversion	<p>Primarily for digital printing. Prints should be left flat for at least 4 hours prior to cutting, lamination or application.</p>			
Precaution	<p>For application to smooth flat surfaces only. For best results ensure product must be printed within 6 months of purchase.</p>			
Application	<p>Wet application.</p>			
Compliance	<p>REACH and RoHS compliant</p>			
Fire Certification	<p>Not Applicable</p>			
Face Material	<p>Monomeric calendered PVC</p>			
Face Thickness	<p>150µ thick</p>			
Adhesive	<p>N/A</p>			
Adhesive weight	<p>N/A</p>			
Perceived Tack	<p>Low Tack Repositionable / Removable</p>			
Liner	<p>190gsm PE cling liner</p>			
Dimensional stability	<p>N/A</p>			
Conformability	<p>1D Flat-sided</p>			
Optimal application temp	<p>+15 to 25°C</p>			
Min application temp	<p>+5°C</p>			
Max application temp	<p>+30°C</p>			
Intermittent service temp	<p>-30 to 100°C</p>			
Shelf-life	<p>0.5 year</p>			
Adhesive Data (Nominal)	180° Peel Adhesion N/25mm			
		Stainless Steel	Glass	Polypropylene
	20 min	<1	<1	0
	24 hour	<1	<1	0
1 week	<1	<1	0	
Chemical Resistance	<p>The unprinted film can be wiped clean with water and diluted household detergents. Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali, diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.</p>			
Outdoor Durability	<p>1 year unprinted Zone 1 (Northern Europe, North America) vertical exposure 0-1 year unprinted Zone 2 (S. Europe, Central & S. America, Asia Pacific) vertical exposure 0-1 year unprinted Zone 3 (Middle East, Africa & desert areas) vertical exposure</p>			
Important	<p>The nominal values shown are based upon research and test methods on unprinted material and are provided without guarantee and do not constitute a warranty. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Actual performance will depend on substrate preparation, exposure conditions and correct application. For further information on the test methods used refer to www.nu-coat.com/testmethods. Nu-Coat Limited will not be liable for any indirect or consequential loss.</p>			