

Description M21-P-X. 80µ gloss clear 5 year monomeric PVC, airXit permanent adhesive, stay flat structured neutral PE liner

'M Series' 5 year monomeric for flat-sides. Gloss Clear monomeric with an 'airXit' clear permanent adhesive on a polyethylene coated liner. The structured liner and adhesive systems speeds up application times and helps to eliminate air bubbles. EN13501-1 and BS 476 Class 0 fire rated.

Key Features Solvent, Latex and UV printable.
For flat mid term surfaces.
Fire rated.
Bubble free dry application.
Available up to 1600mm wide.
Phthalate Free
VOC Free

Conversion Primarily for digital printing but can be CAD cut.

Precaution For application to flat surfaces only.

Application Dry application.

Compliance REACH and RoHS compliant

Fire Certification EN13501-1 and BS 476 Class 0

Face Material Monomeric calendered PVC
Face Thickness 80µ thick
Adhesive 'airXit' PermPLUS permanent clear UV polyacrylate - VOC Free
Adhesive weight Nominal 25gsm
Perceived Tack Medium Tack Repositionable / Permanent
Liner 150gsm structured PE liner
Dimensional stability Nominal 0.13mm
Conformability 1D Flat-sided
Optimal application temp +15 to 25°C
Min application temp +10°C
Max application temp +30°C
Intermittent service temp -30 to 100°C
Shelf-life 2 year

Adhesive Data (Nominal)	180° Peel Adhesion N/25mm			
	Stainless Steel	Glass	Polypropylene	MDF
20 min	12	13	7	4
24 hour	12	13	8	5
1 week	13	14	8	6

Chemical Resistance The unprinted film can be wiped clean with water and diluted household detergents. Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali, diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.

Outdoor Durability 5 year unprinted Zone 1 (Northern Europe, North America) vertical exposure
2-3 year unprinted Zone 2 (S. Europe, Central & S. America, Asia Pacific) vertical exposure
1-2 year unprinted Zone 3 (Middle East, Africa & desert areas) vertical exposure

Important The nominal values shown are based upon research and test methods on unprinted material and are provided without guarantee and do not constitute a warranty. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Actual performance will depend on substrate preparation, exposure conditions and correct application. For further information on the test methods used refer to www.nu-coat.com/testmethods. Nu-Coat Limited will not be liable for any indirect or consequential loss.