

Description 75µ frost effect 4-5 year monomeric PVC, ReMOVE removable adhesive, stay flat neutral PE liner
 4-5 year monomeric for window graphics, featuring a non-milking, when wet applied, ReMOVE removable adhesive. The 'water-repellent' PE coated liner makes wet application easier. Blocks over 65% of harmful UVa light, good stability and excellent light transmission, and good privacy.

Key Features For mid term flat surfaces.
 UVa block 65%.
 Solvent, Latex and UV printable.
 'Water-repellent' PE liner for maximum stability.
 No adhesive milking when wet applied.
 Clean removable from most surfaces after 1 year.
 Phthalate and VOC Free.
 Available up to 1600mm wide.

Conversion Primarily for CAD.
 For Latex printing, users are advised to test print.

Precaution

Application Wet application is highly recommended.

Compliance REACH and RoHS compliant

Fire Certification EN13501-1

Face Material Monomeric calendered PVC
Face Thickness 75µ thick
Adhesive 'ReMOVE' removable clear UV polyacrylate
Adhesive weight Nominal 20gsm
Perceived Tack Low Tack Repositionable / Removable
Liner 140gsm PE liner
Dimensional stability Nominal 3.09mm
Conformability 1D Flat-sided
Optimal application temp +5 to 25°C
Min application temp +2°C on stainless steel or glass
Max application temp +30°C
Intermittent service temp -30 to 100°C
Shelf-life 2 year

Adhesive Data (Nominal)

180° Peel Adhesion N/25mm

	Stainless Steel	Glass	Polypropylene	MDF
20 min	4	4	6	1
24 hour	4	4	6	1
1 week	4	4	6	1

Chemical Resistance

The unprinted film can be wiped clean with water and diluted household detergents. Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali, diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.

Outdoor Durability

4-5 year unprinted Zone 1 (Northern Europe, North America) vertical exposure
 2-3 year unprinted Zone 2 (S. Europe, Central & S. America, Asia Pacific) vertical exposure
 1-2 year unprinted Zone 3 (Middle East, Africa & desert areas) vertical exposure

Important

The nominal values shown are based upon research and test methods on unprinted material and are provided without guarantee and do not constitute a warranty. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Actual performance will depend on substrate preparation, exposure conditions and correct application. For further information on the test methods used refer to www.nu-coat.com/testmethods. Nu-Coat Limited will not be liable for any indirect or consequential loss.