

Description	<p>P65-W-X(N). 75µ frost effect 5 year monomeric PVC, airXit clear window adhesive, structured neutral PE liner</p> <p>'W Series' 5 year monomeric for window graphics, featuring an airXit clear WindowPLUS permanent adhesive. The structured liner and adhesive systems speeds up application times and helps to eliminate air bubbles. Blocks over 65% of harmful UVa light, very good stability and light transmission, and good privacy.</p>				
Key Features	<p>For mid term flat surfaces.                  Solvent, Latex and UV printable.                  Bubble free dry application.                  'Water-repellent' PE liner for maximum stability.                  UVa block 65%.                  Available up to 1600mm wide.                  Phthalate Free                  VOC Free</p>				
Conversion	<p>Primarily for CAD.                  For Latex printing, users are advised to test print.</p>				
Precaution	<p>There is always a risk of leaving adhesive during removal.</p>				
Application	<p>Dry application.</p>				
Compliance	<p>REACH and RoHS compliant</p>				
Fire Certification	<p>EN13501-1</p>				
Face Material	<p>Monomeric calendered PVC</p>				
Face Thickness	<p>75µ thick</p>				
Adhesive	<p>'airXit' WindowPLUS permanent clear UV polyacrylate - VOC Free</p>				
Adhesive weight	<p>Nominal 30gsm</p>				
Perceived Tack	<p>Medium Tack Permanent</p>				
Liner	<p>150gsm structured PE liner</p>				
Dimensional stability	<p>Nominal 0.12mm</p>				
Conformability	<p>1D Flat-sided</p>				
Optimal application temp	<p>+15 to 25°C</p>				
Min application temp	<p>+10°C</p>				
Max application temp	<p>+30°C</p>				
Intermittent service temp	<p>-30 to 100°C</p>				
Shelf-life	<p>2 year</p>				
Adhesive Data (Nominal)	180° Peel Adhesion N/25mm				
		Stainless Steel	Glass	Polypropylene	MDF
	20 min	9	11	5	2
	24 hour	9	11	5	2
	1 week	9	11	5	2
Chemical Resistance	<p>The unprinted film can be wiped clean with water and diluted household detergents. Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali, diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.</p>				
Outdoor Durability	<p>5 year unprinted Zone 1 (Northern Europe, North America) vertical exposure                  2-3 year unprinted Zone 2 (S. Europe, Central &amp; S. America, Asia Pacific) vertical exposure                  2 year unprinted Zone 3 (Middle East, Africa &amp; desert areas) vertical exposure</p>				
Important	<p>The nominal values shown are based upon research and test methods on unprinted material and are provided without guarantee and do not constitute a warranty. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Actual performance will depend on substrate preparation, exposure conditions and correct application. For further information on the test methods used refer to <a href="http://www.nu-coat.com/testmethods">www.nu-coat.com/testmethods</a>. Nu-Coat Limited will not be liable for any indirect or consequential loss.</p>				