

Description	<p>P11-P-K. 75µ gloss white 7 year polymeric PVC, PermPLUS permanent adhesive, 135gsm kraft liner</p> <p>'P Series' 7 year polymeric for simple curved surfaces. Bright white polymeric with a clear PermPLUS permanent adhesive on a kraft liner. EN-13501-1 fire rated.</p>				
Key Features	<p>No adhesive milking when wet applied. Fire rated. Available up to 1600mm wide. Solvent, Latex and UV printable. Splice free rolls. Phthalate Free VOC Free</p>				
Conversion	Primarily for digital printing but can be CAD cut.				
Precaution	For application to flat and simple curved surfaces.				
Application	Dry or Wet application.				
Compliance	REACH and RoHS compliant				
Fire Certification	EN13501-1				
Face Material	Polymeric calendered PVC				
Face Thickness	75µ thick				
Adhesive	PermPLUS' permanent clear UV polyacrylate - VOC Free				
Adhesive weight	Nominal 24gsm				
Perceived Tack	Medium Tack Permanent				
Liner	135gsm kraft liner				
Dimensional stability	Nominal 0.09mm				
Conformability	2D Simple Curves				
Optimal application temp	+5 to 25°C				
Min application temp	+2°C on stainless steel or glass				
Max application temp	+30°C				
Intermittent service temp	-30 to 100°C				
Shelf-life	2 year				
Adhesive Data (Nominal)	180° Peel Adhesion N/25mm				
		Stainless Steel	Glass	Polypropylene	MDF
	20 min	16	17	8	5
	24 hour	19	19	9	6
1 week	20	21	10	7	
Chemical Resistance	The unprinted film can be wiped clean with water and diluted household detergents. Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali, diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.				
Outdoor Durability	<p>7 year unprinted Zone 1 (Northern Europe, North America) vertical exposure</p> <p>3-4 year unprinted Zone 2 (S. Europe, Central & S. America, Asia Pacific) vertical exposure</p> <p>2-3 year unprinted Zone 3 (Middle East, Africa & desert areas) vertical exposure</p>				
Important	<p>The nominal values shown are based upon research and test methods on unprinted material and are provided without guarantee and do not constitute a warranty. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Actual performance will depend on substrate preparation, exposure conditions and correct application. For further information on the test methods used refer to www.nu-coat.com/testmethods. Nu-Coat Limited will not be liable for any indirect or consequential loss.</p>				