NU-COAT	Nu-Coat TECHNICAL DATA SHEET				
Description	P21-P-P. 75µ gloss clear 7 year polymeric PVC, PermPLUS permanent adhesive, stay flat PE liner 'P Series' 7 year polymeric for simple curved surfaces. Gloss clear polymeric with a clear PermPLUS permanent adhesive on a stay flat PE liner. Can be used as either a print vinyl or a matched gloss laminate to our 'P Series' polymeric vinyls. EN-13501-1 fire rated.				
	Solvent, Latex and UV printable. Fire rated. For long term curved surfaces. Can also be used as a laminate for eco-solvent, latex and UV with a UVa block of 67% No adhesive milking when wet applied. Available up to 1600mm wide.				
	Primarily for digital printing but can be CAD cut.				
	For application to flat and simple curved surfaces. Dry or Wet application.				
Compliance Fire Certification	REACH and RoHS compliant EN13501-1				
Adhesive weight Perceived Tack Liner Dimensional stability Conformability Optimal application temp	'PermPLUS' permanent clear UV polyacrylate Nominal 24gsm Medium Tack Permanent 140gsm PE liner Nominal 0.09mm 2D Simple Curves +5 to 25°C +2°C on stainless steel or glass +30°C -30 to 100°C				
Adhesive Data (Nominal)		18	0° Peel Adhesion N/25m	nm	
	20 min 24 hour 1 week	Stainless Steel 16 19 20	Glass 17 19 21	Polypropylene 8 9 10	MDF 5 6 7
Chemical Resistance	The unprinted film can be wiped clean with water and diluted household detergents. Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali, diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.				
Outdoor Durability	7 year unprinted Zone 1 (Northern Europe, North America) vertical exposure 3-4 year unprinted Zone 2 (S. Europe, Central & S. America, Asia Pacific) vertical exposure 2-3 year unprinted Zone 3 (Middle East, Africa & desert areas) vertical exposure				
Important	guarantee and do not co compromised by detern low temperatures in the performance will depen	onstitute a warranty. Us nining the suitability of e presence of chemicals d on substrate preparat	ers are advised to ensur each product prior to its i such as solvents, acids e ion, exposure conditions	on unprinted material and re that performance and re that performance and restance of the transfer of the tran	eliability are not exposure to high and deterioration. Actual for further information