NU-COAT	Nu-Coat TECHNI <i>CA</i>	AL DATA SHEET		S11-Z
Description	S11-Z Cling2 150µ gloss whit	te static PVC, 190gsm neutra	I PE cling liner	
	Cling2 White is a smooth, gloss white phthalate free highly plasticised monomeric calendered PVC film formulated for use with leading roll fed printers and sheet fed presses. For self-cling internal and external graphics on windows and other smooth surfaces. Print side face out.			
Key Features	No adhesive so no adhesive residue on removal. Adheres well to smooth surfaces. Available up to 1370mm wide. Solvent, Latex and UV printable. Splice free rolls.			
Conversion	Primarily for digital printing.			
Precaution	For application to smooth flat surfaces only. For best results ensure product must be printed within 6 months of purchase.			
Application	Wet application.			
Compliance	REACH and RoHS compliant			
Fire Certification	Not Applicable			
	N/A N/A Low Tack Repositionable / Removable 190gsm PE cling liner N/A 1D Flat-sided +15 to 25°C +5°C +30°C -30 to 100°C			
Adhesive Data (Nominal)				
Autiesive Data (Nottililal)	1	Stainless Steel	Glass	Polypropylene
	20 min	<1	<1	0
	24 hour	<1	<1	0
	1 week	<1	<1	0
Chemical Resistance	fats and fuels, aliphatic solvents, mild acids, salt and alkali, diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.			
Outdoor Durability	1 year unprinted Zone 1 (Northern Europe, North America) vertical exposure 0-1 year unprinted Zone 2 (S. Europe, Central & S. America, Asia Pacific) vertical exposure 0-1 year unprinted Zone 3 (Middle East, Africa & desert areas) vertical exposure			
Important	The nominal values shown are based upon research and test methods on unprinted material and are provided without guarantee and do not constitute a warranty. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Actual performance will depend on substrate preparation, exposure conditions and correct application. For further information on the test methods used refer to <a href="https://www.nu-coat.com/testmethods">www.nu-coat.com/testmethods</a> . Nu-Coat Limited will not be liable for any indirect or consequential loss.			
	NU-COAT LTD	Doc: S11-Z Rev: 4	Date: 25/04/2024	