



Description S21-Z Cling2 150µ gloss clear static PVC, 190gsm neutral PE cling liner

Cling2 Clear is a smooth, gloss clear phthalate free highly plasticised monomeric calendered PVC film formulated for use with leading roll fed printers and sheet fed presses. For self-cling internal and external graphics on windows and other smooth surfaces. Print side face out.

Key Features No adhesive so no adhesive residue on removal.
Adheres well to smooth surfaces.
Available up to 1370mm wide.
Solvent, Latex and UV printable.
Splice free rolls.

Conversion Primarily for digital printing.

Precaution For application to smooth flat surfaces only.
For best results ensure product must be printed within 6 months of purchase.

Application Wet application.

Compliance REACH and RoHS compliant

Fire Certification Not Applicable

Face Material Monomeric calendered PVC
Face Thickness 150µ thick
Adhesive N/A
Adhesive weight N/A
Perceived Tack Low Tack Repositionable / Removable
Liner 190gsm PE cling liner
Dimensional stability N/A
Conformability 1D Flat-sided
Optimal application temp +15 to 25°C
Min application temp +5°C
Max application temp +30°C
Intermittent service temp -30 to 100°C
Shelf-life 0.5 year

Adhesive Data (Nominal)

180° Peel Adhesion N/25mm

	Stainless Steel	Glass	Polypropylene
20 min	<1	<1	0
24 hour	<1	<1	0
1 week	<1	<1	0

Chemical Resistance The unprinted film can be wiped clean with water and diluted household detergents. Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali, diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.

Outdoor Durability 1 year unprinted Zone 1 (Northern Europe, North America) vertical exposure
0-1 year unprinted Zone 2 (S. Europe, Central & S. America, Asia Pacific) vertical exposure
0-1 year unprinted Zone 3 (Middle East, Africa & desert areas) vertical exposure

Important The nominal values shown are based upon research and test methods on unprinted material and are provided without guarantee and do not constitute a warranty. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Actual performance will depend on substrate preparation, exposure conditions and correct application. For further information on the test methods used refer to www.nu-coat.com/testmethods. Nu-Coat Limited will not be liable for any indirect or consequential loss.